

Hyflon® PFA P450

perfluoroalkoxy

Hyflon PFA is a unique family of semi-crystalline, melt processable perfluoropolymers which combine excellent mechanical characteristics to unique properties such as chemical inertness, heat resistance, inherent flame resistance, low surface energy, and exceptional dielectric properties. Hyflon PFA resins have been designed to retain their properties over a wide range of temperatures from cryogenic to 250-260°C (482-500°F) and are the material of choice in applications such as linings in the Chemical Process Industry,

specialty cables, semiconductor industry, aerospace, and other challenging industries.

Hyflon PFA P450 is a medium molecular weight, high melt flow rate multi purpose resin designed for cable extrusion and injection molding. Hyflon PFA P450 has obtained UL758 recognition for continuous use at 260°C (500°F) and is an ASTM D3307 - Type I resin.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • North America	• South America
Features	• Flame Retardant • High Flow	• High Heat Resistance • Medium Molecular Weight	• Semi Crystalline
Uses	• Aerospace Applications • Cable Jacketing	• Liners • Semiconductor Molding Compounds	
Agency Ratings	• ASTM D 3307 Type I	• UL 758	
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Physical

	Typical Value Unit	Test Method
Specific Gravity	2.12 to 2.17 g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (372°C/5.0 kg)	10 to 17 g/10 min	ASTM D1238

Mechanical

	Typical Value Unit	Test Method
Tensile Modulus ¹ (23°C)	500 to 600 MPa	ASTM D1708
Tensile Strength (Break, 23°C)	> 21.0 MPa	ASTM D1708
Tensile Elongation (Break, 23°C)	> 280 %	ASTM D1708
Flex Life (300.0 µm)	4.0E+3 to 6.0E+3 Cycles	ASTM D2176

Impact

	Typical Value Unit	Test Method
Charpy Notched Impact Strength	No Break	ASTM D256

Hardness

	Typical Value Unit	Test Method
Durometer Hardness (Shore D)	55 to 60	ASTM D2240

Thermal

	Typical Value Unit	Test Method
Max. Continuous Use Temperature	260 °C	
Melting Temperature	300 to 310 °C	ASTM D3307
Peak Crystallization Temperature (DSC)	275 to 285 °C	DSC
CLTE - Flow	0.00012 to 0.00020 cm/cm/°C	ASTM D696
Specific Heat (23°C)	900 to 1100 J/kg/°C	DSC
Thermal Conductivity (40°C)	0.20 W/m/K	ASTM C177
Crystallization Heat	25.0 to 35.0 J/g	DSC
Heat of Fusion	25.0 to 35.0 J/g	DSC

Electrical

	Typical Value Unit	Test Method
Surface Resistivity	> 1.0E+17 ohm	ASTM D257
Volume Resistivity	> 1.0E+17 ohm·cm	ASTM D257

Electrical	Typical Value Unit	Test Method
Dielectric Strength	35 to 40 kV/mm	ASTM D149
Dielectric Constant		ASTM D150
23°C, 50 Hz	2.10	
23°C, 100 kHz	2.10	
Dissipation Factor		ASTM D150
23°C, 50 Hz	< 0.00050	
23°C, 100 kHz	< 0.00050	
Flammability	Typical Value Unit	Test Method
Flame Rating - UL	V-0	UL 94
Oxygen Index	95 %	ASTM D2863

Additional Information**PROCESSING**

- Because PFA is corrosive in the melt, machinery used to process Hyflon should be lined with corrosion resistant alloys. Clean, reworked material can be used up to 25% in weight.

HEALTH SAFETY AND ENVIRONMENT

- Hyflon PFA P450 is a very inert polymer and it is not harmful if used and handled according to standard processing procedures. If handled inappropriately, it may release harmful toxic chemicals. Please refer to the Material Safety Data Sheets for more information on handling and safety.

PACKAGING AND STORAGE

- Hyflon PFA P450 resin is available in 25 kg (55 lbs) and 500 kg (1102 lbs) packaging. Though it has an indefinite shelf life, it is recommended to store it in a clean area, protected by direct sun light and possible contamination.

Notes

Typical properties: these are not to be construed as specifications.

¹ 1.0 mm/min

www.SolvaySpecialtyPolymers.com

Contact Solvay Specialty Polymers

Europe, Middle East and Africa SpecialtyPolymers.EMEA@solway.com
Americas SpecialtyPolymers.Americas@solway.com
Asia and Australia SpecialtyPolymers.Asia@solway.com

For assistance with an emergency involving this product, such as spill, leak, fire or explosion, call day or night:

Emergency Health Information

USA +1.800.621.4590
International +1.770.772.8577

Emergency Spill Information

USA +1.800.424.9300
+1.703.527.3887 (CHEMTREC)
Europe +44.208.762.8322 (CARECHEM)
China +86.10.5100.3039
All other Asian countries +65.633.44.177

For additional product information, technical assistance and Material Safety Data Sheets (MSDS), call:

USA + 1.800.621.4557 / +1.770.772.8760
Europe +39.02.3835.1
Japan +81.3.5425.4300
China & Southeast Asia +86.21.5080.5080

Material Safety Data Sheets (MSDS) for products of Solvay Specialty Polymers are available upon request from your sales representative or by emailing us at specialtypolymers@solway.com. Always consult the appropriate MSDS before using any of our products.

Solvay Specialty Polymers is comprised of the activities of the Solvay Advanced Polymers, Solvay Solexis and Solvay Padanaplast companies along with the Ixan® and Diofan® PVDC products lines. To our actual knowledge, the information contained herein is accurate as of the date of this document. However the companies that comprise Solvay Specialty Polymers and none of their affiliates make any warranty, express or implied, or accepts any liability in connection with this information or its use. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for implantable medical devices; Solvay Specialty Polymers does not allow or support the use of any other products in any implant applications. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. All companies comprising Solvay Specialty Polymers reserve the right to make additions, deletions or modifications to the information at any time without prior notification.

All trademarks and registered trademarks are property of the companies that comprise Solvay Specialty Polymers or their respective owners.
© 2012 Solvay Specialty Polymers. All rights reserved.

